

Etanchéité de plan de joint Adhesive Systems Inc.

PRODUCT	COLOR	VISCOSITY	GAP FILL	TEMP RANGE	CURE STATE	CURE SPEED (FIXTURE/FULL)	SPECIFIC GRAVITY
TORQUE GM 10	Purple	275,000 cps	.010"-.050"	-65 TO 350ø F	Flexible	15 Min/8 Hours	1.1
TORQUE GM 25	Red	125,000 cps	.010"-.020"	-65 TO 350ø F	Flexible	5 Min/8 Hours	1.2
TORQUE GM 30	Red	800,000 cps	.010"-.050"	-65 TO 350ø F	Flexible	20 Min/8 Hours	1.1
TORQUE GM 35	Green	20,000 cps	.010"-.020"	-65 TO 350ø F	Semi-rigid	90 Min/8 Hours	1.25
TORQUE GM 40	Red	200,000 cps	.010"-.020"	-65 TO 450ø F	Rigid	30 Min/8 Hours	1.16
TORQUE GM 45	Blue	100,000 cps	.010"-.020"	-65 TO 350ø F	Flexible	45 Min/8 Hours	1.12
TORQUE GM 50	Orange	40,000 cps	.010"-.020"	-65 TO 350ø F	Semi-rigid	5 Min/6 Hours	1.11