

Assemblage par emmanchement Adhesive Systems Inc.

PRODUCT	COLOR	VISCOSITY	GAP FILL	SHEAR STRENGTH STEEL/STEEL	TEMP RANGE	CURE SPEED (FIXTURE/FULL)	SPECIFIC GRAVITY
TORQUE 03 RC	Green	125 cps	.005"	3,800 psi	-65 TO 350ø F	10Min/8 Hours	1.1
TORQUE 09 RC	Green	125 cps	.005"	3,800 psi	-65 TO 350ø F	15Min/8 Hours	1.1
TORQUE 20 RC	Green	8,500 cps	.015"	4,000 psi	-65 TO 450ø F	15Min/8 Hours	1.16
TORQUE 35 RC	Green	2,000 cps	.010"	4,200 psi	-65 TO 350ø F	10Min/8 Hours	1.05
TORQUE 38 RC	Green	2,500 cps	.010"	4,500 psi	-65 TO 350ø F	2Min/8 Hours	1.019
TORQUE 40 RC	Green	600 cps	.007"	3,500 psi	-65 TO 450ø F	40 Min/8 Hours	1.12
TORQUE 41 RC	Yellow	750 cps	.010"	1,800 psi	-65 TO 350ø F	15Min/8 Hours	1.07
TORQUE 48 RC	Green	500 cps	.006"	4,000 psi	-65 TO 350ø F	2 Min/8 Hours	1.13
TORQUE 60 RC	Silver	250,000 cps	.020"	3,500 psi	-65 TO 350ø F	10Min/24 Hours	1.13
TORQUE 75 RC	Green	125 cps	.005"	3,500 psi	-65 TO 350ø F	30Min/24 Hours	1.09
TORQUE 80 RC	Green	1,400 cps	.015"	4,200 psi	-65 TO 450ø F	5 Min/8 Hours	1.11