

Freinage anaérobie Adhesive Systems Inc.

PRODUCT	COLOR	VISCOSITY	BREAKAWAY PREVAILING TORQUE	TEMP RANGE	CURE SPEED (FDXTURE/FULL)	SPECIFIC GRAVITY
TORQUE 21 TL	Violet	200 cps LT	40/25	-60 TO 350° F	10 Min/8 Hours	1.08
TORQUE 22 TL	Purple	1,200 cps MT	75/50	-60 TO 350° F	10 Min/8 Hours	1.05
TORQUE 41 TL	Blue	200 cps LT	150/75	-60 TO 350° F	10 Min/8 Hours	1.08
TORQUE 42 TL	Blue	1,200 cps MT	150/75	-60 TO 350° F	10 Min/8 Hours	1.07
TORQUE 43 TL	Blue	5,000 cps MT	180/90	-60 TO 350° F	10 Min/8 Hours	1.08
TORQUE 62 TL	Red	3,500 cps MT	200/275	-60 TO 350° F	10 Min/8 Hours	1.05
TORQUE 71 TL	Red	500 cps MT	250/350	-60 TO 350° F	10 Min/8 Hours	1.12
TORQUE 72 TL	Red	9,000 cps HT	250/375	-60 TO 450° F	15 Min/24 Hours	1.11
TORQUE 77 TL	Red	7,000 cps MT	275/375	-60 TO 350° F	10 Min/8 Hours	1.12
TORQUE 90 TL	Green	12 cps LT	150/275	-60 TO 350° F	10 Min/8 Hours	1.08