

## Cyanoacrylates Adhesive Systems Inc.

General purpose instant adhesives ideal for rubber and plastic bonding.

PRODUCT	BASE	COLOR	GAP FILL	VISCOSITY	STRENGTH	TEMP RANGE	CURE SPEED (FIXTURE/FULL)	SPECIFIC GRAVITY	MIL SPEC A 46050C
RP 5	Ethyl	Clear	0.002	5 cps	2700/4300	-65 to +200° F	<5 Sec/8 Hours	1.05	Type II, Class 1
RP 45	Ethyl	Clear	0.004	45 cps	2700/4300	-65 to +200° F	<10 sec/8 Hours	1.05	Type II, Class 1
RP 100	Ethyl	Clear	0.006	100 cps	2700/4300	-65 to +200° F	<10 Sec/8 Hours	1.05	Type II, Class 2
RP 500	Ethyl	Clear	0.007	500 cps	2700/4300	-65 to +200° F	<10 Sec/8 Hours	1.05	Type II, Class 2
RP 1000	Ethyl	Clear	0.008	1,000 cps	2700/4300	-65 to +200° F	<15 Sec/8 Hours	1.09	Type II, Class 3
RP 4000	Ethyl	Clear	0.008	4,000 cps	2700/4300	-65 to +200° F	<15 Sec/8 Hours	1.09	Type II, Class 3
APS GEL	Ethyl	Clear	0.01	Gel	2700/4300	-65 to +200° F	<25 Sec/8 Hours	1.05	Type II, Class 3

Flacons de 1oz (28.35gr), 2oz (56.70gr) et 1Lb (453.60gr)