

Cyanoacrylates Adhesive Systems Inc.

Applications that require exceptionally fast cure speeds, difficult to bond surfaces, and acidic surfaces.

PRODUCT	BASE	COLOR	GAP FILL	VISCOSITY	STRENGTH	TEMP RANGE	CURE SPEED (FIXTURE/FULL)	SPECIFIC GRAVITY	MIL SPEC A 46050C
SI 5	Ethyl	Clear	0.002	5 cps	2800/4200	-65 to 200° F	<5 Sec/8 Hours	1.05	Type II, Class 1
SI 30	Ethyl	Clear	0.004	30 cps	2800/4200	-65 to 200° F	<5 Sec/8 Hours	1.05	Type II, Class 1
SI 120	Ethyl	Clear	0.006	120 cps	2800/4200	-65 to 200° F	<8 Sec/8 Hours	1.05	Type II, Class 2
SI 500	Ethyl	Clear	0.007	500 cps	2800/4200	-65 to 200° F	<8 Sec/8 Hours	1.05	Type II, Class 2
SI 1000	Ethyl	Clear	0.008	1,000 cps	2800/4200	-65 to 200° F	<8 Sec/8 Hours	1.05	Type II, Class 3
SI 4000	Ethyl	Clear	0.009	4,000 cps	2800/4200	-65 to 200° F	<10 Sec/8 Hours	1.09	Type II, Class 3
SI GEL	Ethyl	Clear	0.01	Gel	2800/4200	-65 to 200° F	<10 Sec/8 Hours	1.05	Type II, Class 3

Flacons de 1oz (28.35gr), 2oz (56.70gr) et 1Lb (453.60gr)