

Cyanoacrylates Adhesive Systems Inc.

Toughened excellent impact resistance and thermocycling properties.
Ideal for bonding dissimilar materials on a wide range of surfaces.

PRODUCT	BASE	COLOR	GAP FILL	VISCOSITY	STRENGTH	TEMP RANGE	CURE SPEED (FIXTURE/FULL)	SPECIFIC GRAVITY	MIL SPEC A 46050C
TS 300	Modified Ethyl	Clear	0.006	300 cps	3750	-65 to+250° F	<10 Sec/8 Hours	1.1	Type II, Class 2
TS 800	Modified Ethyl	Clear	0.008	800 cps	3750	-65 to+250° F	<15 Sec/8 Hours	1.1	Type II, Class 3
TS 2400	Modified Ethyl	Clear	0.01	2,400 cps	3750	-65 to+250° F	<15 Sec/8 Hours	1.1	Type II, Class 3
TS 4000	Modified Ethyl	Clear	0.01	4,000 cps	3750	-65 to+250° F	<18 Sec/8 Hours	1.1	Type II, Class 3

Flacons de 1oz (28.35gr), 2oz (56.70gr) et 1Lb (453.60gr)