

Product Information Sheet

EPO-TEK® HYB-353ND-TX2 (formerly 113-188-2)

Date: 11/5/2015

Rev: IV

Material Description:

A two component, high temperature hybrid epoxy for semiconductor, fiber optic and medical applications. It is designed to have similar cured performance to EPO-TEK® 353ND; modified to allow for initial UV tacking. It is a higher thixotropy version of EPO-TEK® HYB-353ND.

Number of Components: Two

Mix Ratio by Weight: 100 : 3

Recommended Cure: Initial Tack 100mW/cm² for 10 seconds @ 240-365 nm + 150°C/30 Minutes Thermal Cure

Minimum Alternative Cure: Initial Tack 100mW/cm² for 10 seconds @ 240-365 nm + 100°C/30 Minutes Thermal Cure

Initial Tack 100mW/cm² for 10 seconds @ 240-365 nm + 80°C/1 Hour Thermal Cure

Specific Gravity: Part A: 1.14 Part B: 1.09

Pot Life: 2 Days

Shelf Life: Six months at room temperature, protected from light

NOTES:

- Container(s) should be kept closed when not in use.
- To prevent gelation, keep containers away from light sources.
- Filled systems should be stirred thoroughly before mixing and prior to use.
- Performance properties (rheology, conductivity & others) may vary from those stated below when syringe packaging and/or post-processing is required.
- If product crystallizes in storage, place container in warm oven until crystallization disappears. Refer to Tech Tip #7 on website.
- **TOTAL MASS SHOULD NOT EXCEED 25 GRAMS**

MATERIAL CHARACTERISTICS: Cure Condition: Initial Tack 100mW/cm² for 10 seconds @ 240-365nm + 150°C/30 Minutes Thermal Cure
To be used as a guide only, not as a specification. Different batches, conditions and applications yield differing results.

PHYSICAL PROPERTIES:

Color (before cure):	Part A: Cloudy	Part B: Amber	
Consistency:	Pourable liquid		
Viscosity (23°C) @ 10 rpm:	25,310 cPs		
Thixotropic Index:	1.7		
Glass Transition Temp:	105 °C (Dynamic Cure:20-200°C/ISO 25 Min; + Ramp -10-200°C @ 20°C/Min)		
Shore D Hardness:	80		
Die Shear @ 23°C:	17 Kg		
Degradation Temp:	410 °C		
Weight Loss:	@ 200°C	0.05 %	
	@ 250°C	0.50 %	
	@ 300°C	1.50 %	
Suggested Operating Temperature:	<350 °C (Intermittent)		

OPTICAL PROPERTIES @ 23°C:

Spectral Transmission:	≥ 50% @ 550 nm ≥ 95% @ 1,100-1,600 nm ≥ 98% @ 800-1,000 nm (uncured)
-------------------------------	--

This information is based on data and tests believed to be accurate. Epoxy Technology, Inc. makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.