

NOVAGARD[®]

Solutions

Versilube[®] G351[™]

Specification Data

DESCRIPTION

Versilube[®] G351 is a soap-thickened, dimethyl-diphenyl polysiloxane based grease. Formulated to conform with the specifications outlined in MIL L-15719A, Versilube G351 resists oxidation and degradation even under extreme conditions.

APPLICATIONS

Versilube G351 is often used in closed systems (e.g., refrigerators, vacuum cleaners, and electric regions) where trouble free service for the life of the ball bearing may be expected. In addition, Versilube G351 is designed to be radiation resistant with excellent long-term aging and work stability characteristics that make it ideal for use in nuclear power plants

RESTRICTIONS

Do not use in or around highly oxidative chemicals such as liquid oxygen, chlorine or peroxides.

AVAILABILITY

Versilube G351 is available in 5.3 ounce tubes, 1-gallon pails, 5-gallon pails, and 55-gallon drums.

STORAGE

Versilube G351 has a shelf-life of twenty four (24) months from the date of manufacture when stored in the original, unopened container at, or below, 100°F. Upon prolonged storage, it is normal for a small amount of fluid bleed to appear on the surface of the grease. This condition is not detrimental to the performance and the fluid is simply mixed back into the suspension.

PRODUCT SPECIFICATIONS

Physical Property	Test Method	Performance Range
Appearance		Off-white to tan paste
Penetration (worked 60X)	ASTM D 217	260-300
Bleed	150°C / 100 hours	12.0 % maximum
Evaporation	150°C / 50 hours	2.0 % maximum

PRECAUTIONS

Silicone greases may be cleaned with non-polar solvents such as toluene, hexane and mineral spirits. Whenever using solvents be certain to observe all proper, safety precautions. Not for application on surfaces that are to be painted

Consult and obey all applicable local, state and federal regulations for disposal of solvent and silicone waste. For additional information consult product M.S.D.S.

ADDITIONAL INFORMATION

Novagard believes that the information provided is a true and accurate description of the typical characteristics of the aforementioned product; however, it is the responsibility of the individual user to thoroughly test the product in their specific application to determine performance, efficacy and safety.

TYPICAL PROPERTIES*

Physical Property	Test Method	Performance Range
Dropping Point	ASTM D 566	190°C (375°F) minimum
Specific Gravity		1.02 – 1.06
Water Washout	ASTM D 1264	20.0% maximum
Oxygen Stability	150°C / 50 hours	5 psi drop maximum
Low Temperature Torque	-18°C (0°F)	Pass (15 seconds max)
Corrosion	Copper substrate	No effect
Dirt Count		
25 microns or greater		7500 maximum
75 microns or greater		1600 maximum
125 microns or greater		0 maximum

*The values outlined reflect testing that was conducted on laboratory prepared specimens, actual results may vary. The information provided in the above table is not intended for use in preparing specifications. Please consult manufacturer for additional information.

Novagard **Solutions**[™]
5109 Hamilton Avenue
Cleveland, OH 44114

Form Name
10-D3-G351

Phone: (216) 881-3890 Facsimile: (216) 881-6977

Effective Date
07-16-12

www.novagardsolutions.com