

# FTPOLYMER

122 Chemin de la Cavée - 78630 Orgeval  
Tél : +33 (0)1 39 13 20 82 - Fax : +33 (0)1 39 13 33 79

## 200 SERIES RTV PRODUCTS

Product	Description	Application	Color/ Appearance	Shore Hardness	Viscosity	Tack Time	Full Cure Time	Specific Gravity
200-1XX	Self-leveling Non-corrosive Moisture cure	Small areas Joint sealant Crack filler	Color - many Appearance - liquid	25 +/- 5 A	70,000 - 120,000 cps	30 min	24 - 30 hrs	1.10-1.20
200-182	Semi-Self leveling Non-corrosive Encapsulating compound	Electrical devices Mechanical devices Electrical terminals	Red/Liquid	15 +/- 5 A	21,000 - 40,000 cps	60 min	72 hrs	0.95-1.01
200-185	Self-leveling Non-corrosive Encapsulating compound	Custom formulated to flow into small crevices	Orange/Liquid	10 - 16	2,000-4,000 cps	30 min	48 hrs	0.95-1.01
200-186	Extremely low viscosity Non-corrosive Self-leveling	Custom formulated to flow into small crevices	Bright Green/Liquid	10 - 16	2,000-4,000 cps	30 min	48 hrs	0.95-1.01
200-202	Semi-Self leveling Non-corrosive Encapsulating compound	Electrical devices Mechanical devices Electrical terminals	Black/Liquid	15 +/- 5 A	20,000-35,000 cps	20 min	57 - 63 hrs	0.95-1.01
200-465	Self-leveling Non-corrosive Encapsulating compound	Custom formulated to flow into small crevices	Gray/Fluid	25 +/- 5 A	20,000-40,000 cps	5-15 min	24-30 hrs	1.10-1.20
200-250	Semi-Self leveling Non-corrosive Encapsulating compound	Electrical devices Mechanical devices Electrical terminals	Translucent/Liquid	15 +/- 5 A	21,000 - 40,000 cps	60 min	72 hrs	0.95-1.01
200-251	Self-leveling Non-corrosive Encapsulating compound	Electrical devices Mechanical devices Electrical terminals	Translucent/Liquid	20 +/- 5 A	8,000-12,000 cps	20 min	71-73 hrs	0.95-1.01
200-252	Self-leveling Non-corrosive Encapsulating compound	Electrical devices Mechanical devices Electrical terminals	Translucent/Liquid	20 +/- 5 A	38,000-48,000 cps	10 min	24 hrs	0.95-1.01
200-257	Semi-Self leveling Non-corrosive Encapsulating compound	Electrical devices Mechanical devices Electrical terminals	Translucent/Liquid	15 +/- 5 A	70,000 - 120,000 cps	20 min	57 - 63 hrs	0.95-1.01
200-260	Extremely low viscosity Non-corrosive Self-leveling	Electrical devices Mechanical devices Electrical terminals	Translucent/Liquid	20 +/- 5 A	300-800 cps	60 min	24-30 hrs	0.95-1.01