



Preliminary Product Information Sheet

(Note: These are typical properties to be used as a guide only, not a specification. Data below is not guaranteed. Different batches, conditions and applications yield differing results.)

MATERIAL ID:	EPO-TEK® OG116
Date:	Sep 2013
Rev:	III
Material Description:	A single component, UV cured, high viscosity adhesive for opto-electronic applications including fiber optic packaging, sensor device, SCI-OEM optics and general electronic assembly. Notable qualities include high Tg and index of refraction.
Number of Components:	Single
Mix Ratio by Weight:	N/A
Recommended Cure:	100mW/cm ² @ 240-365 for > 2 minutes, depending on thickness - under an F-type Mercury lamp
Specific Gravity:	1.20
Pot Life:	N/A
Shelf Life:	One year at room temperature

NOTE: Container(s) should be kept closed when not in use. Filled systems should be stirred thoroughly before mixing and prior to use. Thermal post-cure beneficial - contact techserv@epotek.com for recommendations.

MATERIAL CHARACTERISTICS:

PHYSICAL PROPERTIES:	
Color (before cure):	Clear/Colorless
Consistency	Viscous liquid
Viscosity (23°C): @ 2.5 rpm	88,979 cPs
Thixotropic Index:	N/A
Glass Transition Temp:	146 °C
Coefficient of Thermal Expansion (CTE):	
Below Tg:	56 x 10 ⁻⁶ in/in°C
Above Tg:	165 x 10 ⁻⁶ in/in°C
Die Shear @ 23°C:	12.6 Kg
Degradation Temp:	424 °C
Weight Loss:	
@ 200°C	0.19 %
@ 250°C	0.40 %
@ 300°C	0.68 %
Operating Temp:	
Continuous:	- 55°C to 200°C
Intermittent:	- 55°C to 300°C
Storage Modulus:	215,745 psi
Particle Size:	N/A

OPTICAL PROPERTIES @ 23°C:	
Spectral Transmission:	≥ 98% @ 560 - 1660 nm 89% @ 400 nm
Refractive Index (uncured):	1.5733 @ 589 nm
Refractive Index (cured):	1.5892 @ 589 nm

The data above is INITIAL only - it may be changed at anytime, for any reason without notice to anyone. It is provided only as a guide for evaluation/consideration.

*These material characteristics are typical properties that are based on a limited number of samples/batches. All properties are based on the cure indicated above. Some properties may vary as manufactured quantities are scaled up to commercialized production levels.