

Cyanoacrylates Adhesive Systems Inc.

Low odor/low bloom instant adhesive.
Eliminates frosting and odors typically associated with cyanoacrylates.

PRODUCT	BASE	COLOR	GAP FILL	VISCOSITY	STRENGTH	TEMP RANGE	CURE SPEED (FIXTURE/FULL)	SPECIFIC GRAVITY
NI 5E	Modified	Clear	0.002	5 cps	1900/2700	-65 to +180° F	<10 Sec/24 Hours	1.1
NI 100E	Modified	Clear	0.006	5 cps	1900/2700	-65 to +180° F	<10 Sec/24 Hours	1.1
NI 500E	Modified	Clear	0.007	500 cps	1900/2700	-65 to +180° F	<25 Sec/24 Hours	1.1
NI 1000E	Modified	Clear	0.008	1,000 cps	1900/2700	-65 to +180° F	<10 Sec/24 Hours	1.1

Flacons de 1oz (28.35gr), 2oz (56.70gr) et 1Lb (453.60gr)